

IRON RAW MATERIALS CONDITION MONITORING SAMPLE KITS

IRON PELLETS

Element	Remark
Fe (Total)	65-66 Min-Max.
FeO	1 Max.
SiO ₂	2.5 Max.
Al ₂ O ₃	1 Max.
P	0.1 Max.
S	0.01 Max.
Item	Guaranteed
Tumbler index (%+6.3 mm)	0.95
Cold Compression Strength	250 Min.
Size distribution % + 9.5-16 mm	90%
Porosity	1924

SADRA

Iron Pellets

Sadra International Holding

Site: <https://www.sadraholding.com>

Email: info@sadraholding.com

Office: +98-7644455111

Fax: +98-7644455222

Whats_app numbers: +98-9120920617



SADRA



SCAN ME



Sample ID : 1400254

